



ANDERSON BROS. & JOHNSON

WAUSAU, WI
800-826-1581

COMPRESSIVE
STRENGTH (C 170)

22,350 PSI

MODULUS OF
RUPTURE (C 170)

2,705 PSI

ABSORPTION BY
WEIGHT (C 97)

0.1%

DENSITY
(C 97)

166.6 lbs/ft³



* Photo reproductions may not accurately
match granite colors, final selections
should be made from actual samples.