

ANDERSON BROS. & JOHNSON

COMPRESSIVE
STRENGTH (C 170)

22,010 PSI

MODULUS OF
RUPTURE (C 170)

1,945 PSI

ABSORPTION BY
WEIGHT (C 97)

0.3%

DENSITY
(C 97)

163.5 lbs/ft³



WAUSAU, WI
800-826-1581

* Photo reproductions may not accurately
match granite colors, final selections
should be made from actual samples.

S
I
E
R
R
A

R
O
S
E

G
R
A
N
I
T
E

